

VIGOR

凝膠時間測試機 GEL TESTER



VGT-22

特性:

1. 依據IPC2.3.18(4.1)規範製作
2. 溫度控制精確，不變化
3. 盤面特殊鋼材製作，鍍硬鉻處理不起刮痕
4. 附馬錶計時功能，操作更方便。

FEATURES:

1. well designed tester all following IPC 2.3.18 (4.1) test method requirement.
2. the temp of hot disk is quite stable and veary accurate at $171^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$ ($340^{\circ}\text{F} \pm 0.9^{\circ}\text{F}$)
3. Special design hot disk, harden chrome-plated never scratched.
4. Machine equipped with counter device, to enable operation more convenient.

※Refer/IPC 2.3.18 Gel time for prepreg materials
4.1 Platen. Hot plate or melting point apparatus capable of maintaining a temperature of $171^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$ ($340^{\circ}\text{F} \pm 0.9^{\circ}\text{F}$)

規 格 表 SPECIFICATION

項 目 ITEM	型 號 MODEL	VGT-22
熱 盤 精 度	Platen temp accuracy	$\pm 0.5^{\circ}\text{C}$
指 示 經 度	Temp indicator resolution	$\pm 0.1^{\circ}\text{C}$
電 壓	Power supply	1 ϕ 110V
耗 電 量	Power consumption	300W
操 作 範 圍	Operation	$\phi 50 \text{ mm}$



活全機器股份有限公司

VIGOR MACHINRY CO.,LTD.

TEL: 886-4-2331-3388

FAX: 886-4-2331-3377

<http://www.supvigor.com.tw>

E-mail: c.s.huang@seed.net.tw

工廠地址：台中縣霧峰鄉五福路798號

No. 798, Wu-Fu Road, Wu-Fung Hsiang, Tai-Chung Hsien, Taiwan .

公司地址：台中市西屯區漢成街66號

No. 66, Han-cheng St., his-tun Dist., Taichung, Taiwan .